

Client's ref.: AU91181  
File: 0632-8724usf /Felicia

## TITLE

### METHOD AND SYSTEM OF BEAM ENERGY CONTROL

#### BACKGROUND OF THE INVENTION

##### Field of the Invention

5           The present invention relates to a thin film transistor manufacturing process and in particular to a method of controlling the beam energy employed therein.

##### Description of the Related Art

10           Thin film transistors (TFT) are widely used to drive conventional liquid crystal display devices. Usually, a thin film transistor (TFT) comprises an amorphous silicon thin film transistor (a-Si:H TFT) and a polysilicon thin film transistor (poly-Si TFT) divided into a high temperature poly silicon (HTPS) transistor and a low  
15           temperature poly silicon (LTPS) transistor.

            Conventionally, in the manufacturing process of the low temperature poly silicon (LTPS) transistor, excimer laser annealing (ELA) is usually performed on amorphous silicon, such that amorphous silicon is recrystallized as  
20           crystal silicon. The crystal silicon is subsequently processed for a transistor. Accordingly, ELA is a key technique when manufacturing low temperature poly silicon (LTPS).

            However, the amount of beam energy absorbed by  
25           amorphous silicon for crystallization depends on the thickness of amorphous silicon. Different amounts of beam energy are absorbed by amorphous silicon of different thicknesses. Thus, the beam energy has to be

controlled depending on the thickness of amorphous silicon. Furthermore, hydrogen explosion can occur during ELA when the hydrogen content exceeds the critical hydrogen content limit, depending on the material. Both  
5 thickness and hydrogen content must be measured and referenced before ELA.

#### SUMMARY OF THE INVENTION

Accordingly, an object of the present invention is to provide a method and system of automatic beam energy  
10 control, such that not only can thickness and hydrogen content of an amorphous silicon be measured, but also ELA can be performed.

Another object of the present invention is to provide a method and system of automatic beam energy  
15 control to provide appropriate beam energy in amorphous silicon of different thicknesses, such that amorphous silicon can reconstitute as crystal silicon.

Still another object of the present invention is to provide a method and system of automatic beam energy  
20 control to avoid hydrogen explosion during ELA.

Further, another object of the present invention is to provide a method and system of automatic beam energy control to reduce failure in the silicon substrate after ELA and enhance yield.

25 One feature of the present invention is determination of whether hydrogen content of amorphous silicon is less than the critical hydrogen content limit to avoid hydrogen explosion before ELA. The critical hydrogen content limit of amorphous silicon varies with

thickness. When the hydrogen content exceeds the critical hydrogen content limit, hydrogen explosion occurs during ELA.

Another feature of the present invention is to set  
5 up a database of beam energy absorbed by amorphous silicon of different thicknesses during crystallization. The appropriate beam energy is found and provided to the amorphous silicon after checking the hydrogen content.

To achieve the above objects, one aspect of the  
10 present invention provides a method of automatic beam energy control. First, a substrate is provided. Next, hydrogen content of the substrate is measured. A warning is issued when hydrogen content exceeds a critical hydrogen content limit. Substrate thickness is measured  
15 when hydrogen content does not exceed the critical hydrogen content limit. A database comprising a plurality of beam energy values individually absorbed by substrates of different thicknesses is set up. A beam energy value corresponding to the measured thickness is  
20 estimated by the database. Finally, a beam energy level is provided for the substrate accordingly.

Another aspect of the present invention provides a system of automatic beam energy control, comprising a substrate holding apparatus, a measurement apparatus, a  
25 comparing apparatus, and a energy beam apparatus. The measurement apparatus measures thickness and hydrogen content of the substrate in the substrate holding apparatus. The comparing apparatus provides a database comprising critical hydrogen content limits and  
30 appropriate beam energy levels for substrates of

different thicknesses, allowing determination of whether a measured hydrogen content value exceeds the critical hydrogen content limit and to provide an appropriate beam energy level. The energy beam apparatus delivers beam energy to the substrate accordingly.

A detailed description is given in the following embodiments with reference to the accompanying drawings.

#### **BRIEF DESCRIPTION OF THE DRAWINGS**

The present invention can be more fully understood by reading the subsequent detailed description and examples with references made to the accompanying drawings, wherein:

FIG. 1 is a block diagram illustrating the system of automatic beam energy control according to one embodiment of the invention;

Fig. 2 is a flowchart illustrating the method of automatic beam energy control according to one embodiment of the invention.

#### **DETAILED DESCRIPTION OF THE INVENTION**

A preferred embodiment of the present invention is now described with reference to the figures.

Fig. 1 illustrates the system of automatic beam energy control according to one embodiment of the present invention. The system comprises a substrate holding apparatus 100, a measurement apparatus 102, a comparing apparatus 104, and a energy beam apparatus 106.

The substrate holding apparatus 100 fixes a substrate, such as amorphous silicon suitable for a thin

film transistor (TFT). The substrate can be transported to the measurement apparatus 102 and a energy beam apparatus 106 by the substrate holding apparatus 100.

5 The measurement apparatus 102 measures thickness and hydrogen content of the substrate. The measurement apparatus 102 preferably uses ellipsometry to measure a light extinction coefficient of the substrate, such that hydrogen content is calculated in accordance with the relationship between the light extinction coefficient and a bandgap of the substrate. As well, thickness is  
10 calculated in accordance with a refractive index of the substrate, also measurable using ellipsometry.

In *Amorphous and Liquid Semiconductors*, Tauc J., 1974, proposes the following formula.

$$\begin{aligned} N_H &= C \cdot A \int_{\omega} [\alpha(\omega) / \omega] d\omega \\ \alpha(\omega) &= B(\hbar\omega - E_g^{OPT})^2 / \hbar\omega \\ A &= [1 + 2(\epsilon_s / \epsilon_0)]^2 (\epsilon_s / \epsilon_0)^{1/2} / 9(\epsilon_s / \epsilon_0)^2 \\ &\text{for aSi } \epsilon_s / \epsilon_0 = 12 \end{aligned}$$

15

$N_H$  indicates hydrogen content of an amorphous silicon, and  $\alpha(\omega)$  is an absorbing coefficient, a function of light frequency.  $\epsilon_s$  is a dielectric constant of a material, and  $\epsilon_0$  is the dielectric constant in a vacuum.  
20  $E_g^{OPT}$  is the energy bandgap of amorphous silicon. B, C, h are all constant.

The hydrogen content  $N_H$  is relative to the absorption coefficient  $\alpha(\omega)$  and energy bandgap  $E_g^{OPT}$ . Extinction coefficient  $k$ , reflection index  $n$ , and thickness can all  
25 be measured by ellipsometry. Furthermore,  $k = [\lambda\alpha(\omega)] / (4\pi)$ . Thus, ellipsometry can be employed to not only measure thickness, but also hydrogen content.

The comparing apparatus 104, comprising a computer, provides a database of critical hydrogen content limits and appropriate beam energy levels for substrates of different thicknesses. Hydrogen content  $T_1$  measured by measurement apparatus 102 is provided to the comparing apparatus 104, as shown in Fig. 1. The comparing apparatus 104 issues a warning or alarm when hydrogen content  $T_1$  exceeds the critical hydrogen content limit. According to the path of  $T_2$ , the comparing apparatus 104 instructs the measurement apparatus 102 to measure thickness  $T_3$  when hydrogen content  $T_1$  does not exceed the critical hydrogen content limit. The amorphous silicon substrate is transported to the measurement apparatus 102 by the substrate holding apparatus 100 according to the path of  $A_1$ . Thickness  $T_3$  measured by the measurement apparatus 102 is then provided to the comparing apparatus 104. According to thickness  $T_3$ , the appropriate beam energy level of amorphous silicon is determined by the comparing apparatus 104. According to the path of  $T_4$ , the appropriate beam energy level is provided to the energy beam apparatus 106 by the comparing apparatus 104.

The energy beam apparatus 106 delivers beam energy to the substrate for ELA. The amorphous silicon substrate is transported to the energy beam apparatus 106 by the substrate holding apparatus 100 according to the path of  $A_2$ . After the appropriate beam energy level is received, ELA is performed in the amorphous silicon substrate by the energy beam apparatus 106 accordingly.

Fig. 2 is a flowchart of the method of automatic beam energy control according to one embodiment of the present invention.

In step S200, the substrate is provided on the  
5 substrate holding apparatus 100.

Next, in step S202, a hydrogen content value  $T_1$  of the substrate is measured by the measurement apparatus 102 after the substrate is transported to the measurement apparatus 102 by the substrate holding apparatus 100.

10 In step S204, the result of hydrogen content  $T_1$  is transported to the comparing apparatus 104 to determine if hydrogen content  $T_1$  exceeds a critical hydrogen content limit.

In step S206, a warning or alarm is issued when  
15 hydrogen content  $T_1$  exceeds a critical hydrogen content limit.

In step S208, thickness  $T_3$  of the substrate is measured when hydrogen content  $T_1$  does not exceed a critical hydrogen content limit.

20 In step S210, the appropriate beam energy level  $T_4$  for amorphous silicon of a certain thickness  $T_3$  is determined by the comparing apparatus 104 after measuring thickness  $T_3$ . Requisite beam energy levels for amorphous silicon of varying thicknesses are shown in Table 1. The  
25 appropriate beam energy level  $T_4$  is provided to the energy beam apparatus 106.

**Table 1**

Appropriate beam energy level (mJ)	Thickness of amorphous silicon ( $\text{\AA}$ )
200	100
210	200

220	300
250	400
270	500
290	600
310	700
350	800
400	900
460	1000

Finally, in step S212, beam energy is provided to the substrate according to the beam energy value  $T_4$  by the energy beam apparatus 106. Thus, amorphous silicon becomes crystal silicon after ELA.

5           While the invention has been described by way of example and in terms of the preferred embodiments, it is to be understood that the invention is not limited to the disclosed embodiments. To the contrary, it is intended to cover various modifications and similar arrangements  
10 (as would be apparent to those skilled in the art). Therefore, the scope of the appended claims should be accorded the broadest interpretation so as to encompass all such modifications and similar arrangements.